

# Tyfo<sup>®</sup> S-T

## High Temperature Saturant Epoxy

### DESCRIPTION

The Tyfo<sup>®</sup> S-T Epoxy is a two-component epoxy matrix material for high temperature applications. It is a high elongation material which gives optimum properties as a matrix for the Tyfo<sup>®</sup> Fibrwrap<sup>®</sup> Systems. It provides a short working time for application, with no offensive odor.

### USE

The Tyfo<sup>®</sup> S-T Epoxy matrix material is combined with the Tyfo<sup>®</sup> fabrics to provide a wet-layup composite system for strengthening structural members.

### ADVANTAGES

- Excellent high temperature properties
- Short working time
- High elongation
- 100% solvent-free

### PACKAGING

Order pre-measured units:  
Part A: 5-gallon container  
Part B: 1-gallon container  
One kit yields 3.75 gallons

### MIX RATIO

100.0 parts of component A to 33.1 parts of component B by volume. (100 parts of component A to 26.6 parts of component B by weight).

### SHELF LIFE

Two years in original, unopened and properly stored containers.

### STORAGE CONDITIONS

Store at 60° to 90° F (16° to 32° C). Avoid freezing.

### CERTIFICATE OF COMPLIANCE

- Will be supplied upon request, complete with state and federal packaging laws with copy of labels used.
- Material safety data sheets will be supplied upon request.

### HOW TO USE THE TYFO<sup>®</sup> S-T Epoxy

#### INSTALLATION

Tyfo<sup>®</sup> Systems to be installed by Fyfe Co. LLC trained and certified applicators. Installation shall be in strict compliance with the Fyfe Co. LLC Quality Control Manual.

#### SURFACE PREPARATION

The required surface preparation is largely dependent on the type of element being strengthened. In general, the surface must be clean, dry and free of protrusions or cavities, which may cause voids behind the Tyfo<sup>®</sup> composite. Column surfaces that will receive continuous wraps typically require only a broom cleaning. Discontinuous wrapping surfaces (walls, beams, slabs, etc.) typically require a light sandblast, grinding or other approved methods to prepare for bonding. Mechanical anchors are incorporated in some designs. The Fyfe Co. LLC engineering staff will provide the proper specifications and details based on the project requirements.

### MIXING

Use 100.0 parts of component A to 33.1 parts of component B by volume (100 parts of component A to 26.6 parts of component B by weight). Do not thin; solvents will prevent proper cure. Mix thoroughly for five minutes with a low speed mixer at 400-600 RPM until uniformly blended. When using as a prime coat or finish coat, Tyfo<sup>®</sup> S-T Epoxy may be thickened in the field to the desired consistency.

### APPLICATION

Tyfo<sup>®</sup> S-T Epoxy is applied to a variety of Tyfo<sup>®</sup> fabrics using approved hand-applied methods. Hand saturation is allowable, provided the epoxy is applied uniformly and meets the specifications. Tyfo<sup>®</sup> S-T Epoxy can also be applied as a prime coat by brush or roller. Epoxy must be properly post cured to achieve desired properties. Contact Fyfe Co. engineers for cure schedule.

### LIMITATIONS

Minimum application temperature of the epoxy is 68° F (20° C). **DO NOT THIN**; solvents will prevent proper cure.

### EPOXY MATERIAL PROPERTIES

PROPERTY	ASTM METHOD	TYPICAL TEST VALUE*
Cure Schedule		8 hrs. @ 82 - 85° C or 4 hrs. @ 86 - 93° C
Glass Transition Temperature (T <sub>g</sub> )	E1356	214° F (101° C)
Tensile Strength at Yield	D638 Type 3	11,400 psi (78.6 MPa)
Proportional Limit**	D638 Type 3	6,000 psi (41.4 MPa)
Modulus of Elasticity	D638 Type 3	400,000 psi (2.76 GPa)
Elongation at Break	D638 Type 3	5.0%
Complex Viscosity @ 73° F (23° C)***		5,500 - 6,000 cps
Gel Time @ 73° F (23° C)	(Shyodu Gel Timer)	237 min.
Pot Life @ 73° F (23° C)	Time to 50% increase in viscosity	140 min.
Color	Component A is clear to pale yellow Component B is clear	
Viscosity	Component A at 77° F (25° C) 11,000-13,000 cps Component B at 77° F (25° C) is 15-20 cps	
Density @ 68° F (20° C) (Pound/Gallon)	Component A = 9.7 (1.16kg/L) Component B = 7.8 (0.93kg/L) Mixed Product = 9.2 (1.10kg/L)	

\* Specification values can be provided upon request.

\*\* The stress at which a material exhibits a specified limiting deviation from the proportionality of stress to strain.

\*\*\* Complex viscosity recorded using an oscillating disk rheometer in oscillation mode at 10% strain and a frequency of 1 Hz. Complex viscosity was taken at time < 1.0 min. using parallel plate geometries and a testing gap of 1,000 µm.

## CAUTION!

### COMPONENT A - Irritant:

Prolonged contact to the skin may cause irritation. Avoid eye contact.

### COMPONENT B - Irritant:

Corrosive. Contact with skin may cause severe burns. Avoid eye contact. Product is a strong sensitizer. Use of safety goggles and chemical resistant gloves recommended. Remove contaminated clothing. Avoid breathing vapors. Use adequate ventilation. Use of an organic vapor respirator recommended.

### FIRST AID

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water; contact physician immediately. For respiratory problems, remove to fresh air. Wash clothing before reuse.

### CLEANUP

Collect with absorbent material. Dispose of in accordance with local disposal regulations. Uncured material can be removed with approved solvent. Cured materials can only be removed mechanically.

### SHIPPING LABELS CONTAIN

- State specification number with modifications, if applicable
- Component designation
- Type, if applicable
- Manufacturer's name
- Date of manufacture
- Batch name
- State lot number, if applicable
- Directions for use
- Warnings or precautions required by law

**KEEP CONTAINER TIGHTLY CLOSED.  
NOT FOR INTERNAL CONSUMPTION.  
CONSULT MATERIAL SAFETY DATA SHEET  
(MSDS) FOR MORE INFORMATION.  
KEEP OUT OF REACH OF CHILDREN.  
FOR INDUSTRIAL USE ONLY.**

## Fyfe Co. LLC

Tyfo® Fibrwrap® Systems

3940 Ruffin Road, Suite C, San Diego, CA 92123

Tel: 858.642.0694 Fax: 858.444.2982

E-mail: [info@fyfeco.com](mailto:info@fyfeco.com) [www.fyfeco.com](http://www.fyfeco.com)

**Statement of Responsibility:** The technical information and application advice in this publication is based on the present state of our best scientific and practical knowledge. As the nature of the information herein is general, no assumption can be made as to the product's suitability for a particular use or application, and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by State legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use. Field service, where provided, does not constitute supervisory responsibility. Suggestions made by the Fyfe Co., either verbally or in writing, may be followed, modified or rejected by the owner, engineer or contractor since they, and not the Fyfe Co., are responsible for carrying out procedure appropriate to a specific application.