

# Tyfo<sup>®</sup> SEH-51A Composite using Tyfo<sup>®</sup> SW-1(S) Underwater Epoxy

## DESCRIPTION

The Tyfo<sup>®</sup> SEH-51A Composite is an ICC ER-2103 listed material comprised of Tyfo<sup>®</sup> SW-1(S) Epoxy and Tyfo<sup>®</sup> SEH-51A reinforcing fabric. Tyfo<sup>®</sup> SEH-51A is a custom weave, uni-directional glass fabric used in the Tyfo<sup>®</sup> Fibrwrap<sup>®</sup> System. The glass material is orientated in the 0° direction with additional yellow glass cross fibers at 90°. The Tyfo<sup>®</sup> SW-1(S) Epoxy is a two-component epoxy matrix material. The Tyfo<sup>®</sup> SW-1 epoxy is certified safe for potable water (ANSI/NSF 61) and incidental food contact.

## USE

Tyfo<sup>®</sup> SEH-51A Fabric is combined with Tyfo<sup>®</sup> epoxy material to add strength and ductility to bridges, buildings, and other structures, mainly for areas of moisture and underwater applications.

## ADVANTAGES

- ICC-ES ESR-2103 listed product
- NSF/ANSI Standard 61 listed product for drinking water systems
- Excellent for underwater applications
- Good high & low temperature properties
- High elongation
- Ambient cure
- Rolls can be cut to desired widths prior to shipping

## COVERAGE

Approximately 675 sq. ft. surface area with 3 to 4 units of Tyfo<sup>®</sup> SW-1(S) Epoxy and 1 roll of Tyfo<sup>®</sup> SEH-51A Fabric when used with the Tyfo<sup>®</sup> Saturator.

## PACKAGING

Order Tyfo<sup>®</sup> SW-1(S) Epoxy in pre-measured units in 5-gallon (19L) containers. Order Tyfo<sup>®</sup> SEH-51A Fabric in 54" x 150 lineal foot (1.4m x 45.7m) rolls. Typically ships in 12" x 13" x 64" (305mm x 330mm x 1626mm) boxes.

## EPOXY MIX RATIO

100.0 component A to 56.0 component B by weight. 100.0 component A to 74.0 component B by volume.

## SHELF LIFE

Epoxy - two years in original, unopened and properly stored containers.

Fabric - ten years in proper storage conditions.

## STORAGE CONDITIONS

Store epoxy at 40° to 90° F (4° to 32° C). Avoid freezing. Store rolls flat, not on ends, at temperatures below 100° F (38° C). Avoid moisture and water contamination.

## CERTIFICATE OF COMPLIANCE

- Will be supplied upon request, complete with state and federal packaging laws with copy of labels used.
- Material safety data sheets will be supplied upon request.

### TYPICAL DRY FIBER PROPERTIES

Tensile Strength	470,000 psi (3.24 GPa)
Tensile Modulus	10.5 x 10 <sup>6</sup> psi (72.4 GPa)
Ultimate Elongation	4.5%
Density	0.092 lbs./in. <sup>3</sup> (2.55 g/cm <sup>3</sup> )
Minimum Weight per sq. yd.	27 oz. (915 g/m <sup>2</sup> )

### COMPOSITE GROSS LAMINATE PROPERTIES\*\*

PROPERTY	ASTM METHOD	TYPICAL TEST VALUE	DESIGN VALUE*
Ultimate tensile strength in primary fiber direction	D3039	75,000 psi (517 MPa) (3.75 kip/in. width)	60,000 psi (414 MPa) (3.0 kip/in. width)
Elongation at break	D3039	2.0%	1.6%
Tensile Modulus	D3039	3.411 x 10 <sup>6</sup> psi (23.5 GPa)	2.728 x 10 <sup>6</sup> psi (18.8 GPa)
Ultimate tensile strength 90 degrees to primary fiber	D3039	3,375 psi (23.3 MPa)	2,700 psi (18.6 MPa)
Laminate Thickness		0.05 in. (1.3 mm)	0.05 in. (1.3mm)

\* Gross laminate design properties based on ACI 440 suggested guidelines will vary slightly. Contact Fyfe Co. LLC engineers to confirm project specification values and design methodology.

\*\* Tested after 21 days.

### EPOXY MATERIAL PROPERTIES AT 75° F (24° C)

PROPERTY	TYFO <sup>®</sup> SW-1	TYFO <sup>®</sup> SW-1S
Mixing ratio, by wt.	100:56	100:56
Specific Gravity	1.6	1.1
Viscosity A & B mixed	14,000-18,000 cps	9,000-11,000 cps
Gel Time, 65° F (18° C)	2.5 - 3.5 hours	2.5 - 3.5 hours
<b>ASTM D695, 7 day</b> compressive strength	7,000 - 8,000 psi	7,000 - 8,000 psi
<b>ASTM D695, 7 day</b> compressive strength, mortar (Tyfo <sup>®</sup> SW-1:sand – 1:1 by volume)	8,000 - 9,000 psi	8,000 - 9,000 psi
<b>ASTM D2240</b> Shore D hardness	80 - 85	80 - 85
Values presented are typical laboratory data.		

## HOW TO USE THE TYFO® SW-1(S) COMPOSITE SYSTEM

### DESIGN

The Tyfo® System shall be designed to meet specific design criteria. The criteria for each project is dictated by the engineer of record and any relevant building codes and/or guidelines. The design should be based on the allowable strain for each type of application and the design modulus of the material. The Fyfe Co. LLC engineering staff will provide preliminary design at no obligation.

### INSTALLATION

Tyfo® System to be installed by Fyfe Co. LLC trained and certified applicators. Installation shall be in strict compliance with the Fyfe Co. LLC Quality Control Manual.

### SURFACE PREPARATION

The required surface preparation is largely dependent on the type of element being strengthened. In general, the surface must be clean, dry and free of protrusions or cavities, which may cause voids behind the Tyfo® composite. Column surfaces that will receive continuous wraps typically require only a broom cleaning. Discontinuous wrapping surfaces (walls, beams, slabs, etc.) typically require a light sandblast, grinding or other approved methods to prepare for bonding. Sharp and chamfered corners will be rounded off by grinding or using thickened Tyfo® S Epoxy (Tyfo® WS Epoxy or approved repair mortar). At the time of application, the substrate shall not have any free moisture on it. If moisture cannot be avoided, the use of Tyfo® WP (Wet-Prime epoxy) is recommended. Tyfo® Composite Anchors are incorporated in some designs. The Fyfe Co. LLC engineering staff will provide the proper specifications and details based on the project requirements.

### MIXING

For pre-measured units in 5-gallon (19L) containers, pour the contents of component B into the pail of component A. For drums, premix each component: 100.0 parts of component A to 56.0 parts of component B by weight. Mix thoroughly for five minutes with a low speed mixer at 400-600 RPM until uniformly blended.

### APPLICATION

Apply one prime coat of Tyfo® SW-1(S) Epoxy on the substrate by using a roller. Saturate the fabric by feeding it through the Tyfo® Saturator or by approved hand methods (See the Tyfo® Saturator Manual). Prior to the application of the saturated fabric, fill any uneven surface. Saturate and apply subsequent layers of the fabric according to the Specifications and the Design Requirements. With the use of a roller or hand pressure, ensure proper orientation of fibers. Release or roll out entrapped air and ensure that each individual layer is firmly bedded and adhered to the preceding layer or substrate. Apply a final coat of Tyfo® SW-1(S) Epoxy and detail all fabric edges, including butt splice, termination points and jacket edges.

### LIMITATIONS

Application temperature of the epoxy is a minimum 40° F (4° C) and maximum of 100° F (38° C). DO NOT THIN, solvents will prevent proper cure.

### FIELD QUALITY CONTROL

Record batch numbers for fabric and epoxy used each day and note locations of installations. Measure square feet of fabric and volume of epoxy used each day.

## CAUTION!

### COMPONENT A - Irritant:

Prolonged contact to the skin may cause irritation. Avoid eye contact.

### COMPONENT B - Irritant:

Corrosive. Contact with skin may cause severe burns. Avoid eye contact. Product is a strong sensitizer. Use of safety goggles and chemical resistant gloves recommended. Remove contaminated clothing. Avoid breathing vapors. Use adequate ventilation. Use of an organic vapor respirator recommended.

### SAFETY PRECAUTIONS

Avoid breathing vapors. Avoid contact with eyes and skin. Use of an approved respirator with an organic absorption cartridge is recommended for possible vapors. Rubber gloves, rubber boots, and protective suits are recommended for handling and application of this material. Safety glasses or a face shield are recommended to prevent eye contact.

### FIRST AID

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately. For respiratory problems, remove to fresh air. Wash clothing before reuse.

### CLEANUP

Collect with absorbent material, flush with water. Dispose of in accordance with local disposal regulations. Uncured material can be removed with approved solvent. Cured materials can only be removed mechanically.

### SHIPPING LABELS CONTAIN

- State specification number with modifications, if applicable
- Component designation
- Type, if applicable
- Manufacturer's name
- Date of manufacture
- Batch name
- State lot number, if applicable
- Directions for use
- Warnings or precautions by law

**KEEP CONTAINER TIGHTLY CLOSED.  
NOT FOR INTERNAL CONSUMPTION.  
CONSULT MATERIAL SAFETY DATA SHEET  
(MSDS) FOR MORE INFORMATION.  
KEEP OUT OF REACH OF CHILDREN.  
FOR INDUSTRIAL USE ONLY.**

## Fyfe Co. LLC

Tyfo® Fibrwrap® Systems

3940 Ruffin Road, Suite C, San Diego, CA 92123

Tel: 858.642.0694 Fax: 858.444.2982

E-mail: [info@fyfeco.com](mailto:info@fyfeco.com) [www.fyfeco.com](http://www.fyfeco.com)

**Statement of Responsibility:** The technical information and application advice in this publication is based on the present state of our best scientific and practical knowledge. As the nature of the information herein is general, no assumption can be made as to the product's suitability for a particular use or application, and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by State legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use. Field service, where provided, does not constitute supervisory responsibility. Suggestions made by the Fyfe Co., either verbally or in writing, may be followed, modified or rejected by the owner, engineer or contractor since they, and not the Fyfe Co., are responsible for carrying out procedure appropriate to a specific application.